
Aluminium 1150 Data Sheet

1150 Overview

Alloy 1150 is a non-heat treatable rolled product supplied as rectangular or circular sheet, or coil. 1150 is a soft alloy with very good formability, welding and anodising qualities and with excellent corrosion resistance.

1150 Mass Conversion Factor: Kilograms (kg) per mm per square metre = 2.705kg

Anodising

1150 is very well suited to anodising and is can also be chemically brightened.

Common Applications

1150 is typically used for general sheet metal work where moderate strength is acceptable. Typical applications include metal spinning, cookware, flashing, polished trims and lamp reflectors. Alloy 1050 has similar properties and applications.

*Other common alloys used in metal spinning where higher strengths are required include 6061, 5052 and 3003.

Welding

1150 has excellent weldability by all standard methods. Filler alloy 1100, 4043 and 5356 are common, dependant upon alloy joining combinations.

Machining

Machinability of 1150 is fair in softer tempers though improves as the tempers increase (increasing strength and hardness). Accuracy of machining is managed with high speeds, ample lubrication, sharp tools, positive rakes, adequate clearance and continuous cutting.

Chemical Composition Specification (%) Single values are maxima except as noted

Alloy	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Other	
									Each	Total
1150	0.45	0.45	0.05-0.20	0.05	0.05	-	0.05	0.03	0.030	-
1050*	0.25	0.4	0.05	0.05	0.05	-	0.05	0.03	0.03	
6061	0.4-0.8	0.7	0.15-0.40	0.15	0.8-1.2	0.04-0.35	0.25	0.15	0.05	0.15

*Other specific elements: V 0.05

Mechanical Property Specification - Single values are maxima except as noted

Alloy and Temper	Thickness mm		Tensile Strength				Elongation (% min in 50mm)
	Over	Up to	Ultimate		Yield		
			Min	Max	Min	Max	
1150-H111/O	0.5	3.2	-	105	-	-	20-30
1150-H16	0.5	4	115	150	-	-	2/5
1050-H111/O	0.5	6	-	95	-	-	20-30
1050-H16	0.5	4	115	140	-	-	3-5
6061-O	0.25	3.25	-	150	-	85	14-18

Bend radii

Recommended Minimum Bend Radii for 90-Degree Cold Forming of Sheet of 3003 (Reference test method - ASTM E290) Thickness (t)

Temper	0.8mm	1.6mm	3.2mm	4.8mm	6.0mm
O	0t	0t	0t	1/2t	1t
H12	0t	0t	1/2t	1t	1t
H14	0t	0t	1t	1t	1 1/2t
H16	1t	1t	1 1/2t	2 1/2t	3t
H18	1 1/2t	2t	2 1/2t	3 1/2t	4 1/2t

Bend radii listed are minimum recommendations only for bending sheets without fracture. Application method based on cold forming in a standard press brake with air bend dies. Alternative types of bending operations may require larger radii or smaller radii. Tooling quality and design may vary radii outcomes.

Material Specification & References

AS/NZS 1734:1997 Reconfirmed 2020 – Aluminium and aluminium alloys – Flat sheet, coiled sheet and plate

The information in this data sheet document is not an exhaustive statement of all relevant information and is provided by way of general information only. BlueScope Distribution Pty Ltd makes no representation or warranty in relation to this data sheet document or the products or processes it describes, and takes no responsibility for any adverse consequences of any nature which arise as a result of reliance on the information or recommendations contained in it. You must make your own assessment of the information and recommendations contained in this data sheet document, including when necessary seeking specific advice as to the suitability of the products or processes featured in this data sheet document for the purpose for which, and the manner in which, you propose to use them. This may involve further independent analysis and testing.